SAMWAX® SE-915

Rallychem

Water-based Polyethylene Wax Emulsion 水性聚乙烯蜡乳液

> MATERIAL SPECIFICATION: TYPICAL PROPERTIES: 技术指标

Item	Specification
Form 外观	Light Yellow Liquid 淡黄色液体
Technical Data	
Wax Type 蜡种类	PE Wax 高熔点聚乙烯蜡
Solids Content 固含量	33.5-35.5%
Ionic Character 乳化类型	Non ionic 非离子
Melting Range 软化点	137℃
pH-Value PH 值	8.0-9.0

Properties 性能:

- * Varnish: a great water-based brightener in paper and film packaging 清漆:中蜡比较坚硬,非常适合纸和薄膜包装材料用水性光亮剂
- * Water-based adhesives: suitable for the preparation of water-based adhesives, especially suitable for packaging film (BOPP film, PE film, etc.) and paper sealing glue 水性胶粘剂:适用于制备水基型胶粘剂,一般与 EVA 乳液和增粘树脂一起使用,特别适应于包装覆膜(BOPP 膜、PE 膜等)及水性上光后的纸面接边封口胶
- * Polyurethane coating: improve the anti-friction ability of waterborne polyurethane coatings, such as parquet sealants

聚氨酯涂层: 可提高水性聚氨酯涂层的抗摩擦能力, 如镶木地板的密封剂

- * Printing ink: improve the anti-friction ability of water-based printing ink 可提高水性印刷油墨的耐摩性,减少印刷品表面的摩擦系数度
- * Textile: improve the sewing, anti-friction and tear strength of fabric 提高整理织物的缝纫性、抗摩性、撕破强度
- * Floor Polishes: strengthen hardness and toughness of floor surface, improve its service life

同苯乙烯-丙稀聚合物分散物一起复配使用,可形成干爽、光亮表面。蜡的硬度和韧度使 这些地板蜡抗车印好,使用寿命长

* High compatibility to polymer dispersion, resin solution, plasticizer, film forming agent 与常用的聚合物分散体、树脂溶液、增塑剂、成膜剂配伍性好

Web: www.rallychem.com

Storage 储存:

To be stored at least 12 months under +6-28°C, to avoid frozen and temperature higher than 40°C

本产品至少可在+6-28℃下储存 12 个月以上,避免冷冻及超过 40℃高温

Dosage 用法:

0.5-3% in reference to impregnation method of textile industry 在纺织工业中浸渍法用量大约 0.5-3% 通过搅拌很容易被混合,在生产后阶段加入

Packaging 包装规格:

* 50 KG/Drum * 120 KG/Drum * 1000 KG/Drum



Web: www.rallychem.com