

RL 680TP

Low-Density Oxidized Polyethylene Homopolymer

低密度氧化聚乙烯均聚物



MATERIAL SPECIFICATION:

TYPICAL PROPERTIES:

技术指标

Property	Value
Acid Number 酸值	14-17 mg KOH/g
Drop Point, Mettler 滴点	105-108 °C
Viscosity @ 140°C(284 °F) 粘度	150-250 cps
Hardness @ 25° C (77° F) 针入度	1-2 dmm
Density 密度	0.92-0.95 g/cm ³

APPLICATIONS:

Wax emulsion, PVC processing

蜡乳液, PVC 加工

Rallychem Chemicals

Head Office: Shanghai Rallychem Chemicals Co., Ltd

R&D Center: Jiaxing Rallychem New Material Technology Co., Ltd

Factory: Rallychem New Material (Jiangsu) Co., Ltd

Service Tel: +86-21-63173060

Service Mobil: +86-13456396233

E-mail: info@rallychem.com

瑞勒化学

营销中心: 上海瑞勒化工有限公司

研发中心: 嘉兴瑞勒新材料有限公司

生产中心: 瑞勒新材料(江苏)有限公司

客服热线: +86-21-63173060

客服热线: +86-13456396233

电子邮箱: info@rallychem.com

Website: www.rallychem.com



ISO 9001:2000 Certified