

RL 70

Polyester wax

聚酯蜡



MATERIAL SPECIFICATION:

TYPICAL PROPERTIES:

技术指标

Property	Value
Acid Number 酸值	5-20 mg/KOH
Drop Point, Mettler 滴点	56-62° C
Saponification Value 皂化值	240-270 mg/KOH
Density 密度	0.96 g/cm ³

Property	RL 70
Product Form	Powder 粉末

APPLICATIONS:

PVC calendering external lubricant

PVC 压延外润滑剂

Rallychem Chemicals

Head Office: Shanghai Rallychem Chemicals Co., Ltd

R&D Center: Jiaxing Rallychem New Material Technology Co., Ltd

Factory: Rallychem New Material (Jiangsu) Co., Ltd

Service Tel: +86-21-63173060

Service Mobil: +86-13456396233

E-mail: info@rallychem.com

瑞勒化学

营销中心: 上海瑞勒化工有限公司

研发中心: 嘉兴瑞勒新材料有限公司

生产中心: 瑞勒新材料(江苏)有限公司

客服热线: +86-21-63173060

客服热线: +86-13456396233

电子邮箱: info@rallychem.com

Website: www.rallychem.com



ISO 9001:2000 Certified